



(Attached pages)

(No.) NG24000665

page1of4

|   |   |               |            |             |            |
|---|---|---------------|------------|-------------|------------|
| Test Type   | Commission Test   | Date Received | 2024-07-11 | Date issued | 2024-07-18 |
| Applicant   | Certivision(Xiamen) Ltd., Attention: Yifa Zhong Order No.:SUB2404050  |               |            |             |            |
| Manufacture   | ---   |               |            |             |            |
| Sample Description  | <p>Sample Description: Care Label (CKD81)</p> <p>Submitted Fiber Content: ---</p> <p>Color: ---</p> <p>Claimed Fabric Weight: ---</p> <p>Style/Item#: ---</p> <p>PO No.: ---</p> <p>Buyer/Customer: ---</p> <p>Goods exported to: ---</p> <p>Product End Use: ---</p> <p># of Samples: 18pc(s)</p> <p>Type of Testing: ---</p> <p>Submitted Care Instruction(s):</p>  |               |            |             |            |
| <p>Approved by</p> <p><i>Pei Chen.</i></p> <p>PeiChen(Director)</p> |   |               |            |             |            |
| Notes   | <p>This report is valid only for the samples delivered by clients.</p> <p>The laboratory is not responsible for the sample information authenticity, which is provided by the customer.</p> <p>If there is any objection concerning the report, it is required that the objection should be put forth to the center within 15 days from the reception date of the report.</p> <p>The testing and inspecting results of labels exclude the verification of the authenticity of the contents.</p> |               |            |             |            |



(Attached pages)

(No.) NG24000665

page2of4

| NO. | Items                           | Judgment Basis | Conclusion |
|-----|---------------------------------|----------------|------------|
| 1   | Colour fastness to water        | ---            | —          |
| 2   | Colour fastness to rubbing      | ---            | —          |
| 3   | Colour fastness to perspiration | ---            | —          |
| 4   | Colour fastness to washing      | ---            | —          |
| 5   | Colour fastness to dry cleaning | ---            | —          |



|  |           | Requirement | Results | Judgement |
|--|-----------|-------------|---------|-----------|
| <b>1 Colour fastness to water(Grade) *AATCC 107-2013(2016)</b>       |           |             |         | —         |
| Color change   |           | —           | 4.5     |           |
| Staining   | Acetate   | —           | 4.5     |           |
|  | Cotton    | —           | 4.5     |           |
|  | Polyamide | —           | 4.5     |           |
|  | Polyester | —           | 4.5     |           |
|  | Acrylic   | —           | 4.5     |           |
|  | Wool      | —           | 4.5     |           |
| Self-Staining  |           | —           | 4.5     |           |
| <b>2 Colour fastness to rubbing(Grade) *AATCC 116-2013</b>           |           |             |         | —         |
| dry rubbing  |           | —           | 4.5     |           |
| wet rubbing  |           | —           | 4.5     |           |
| <b>3 Colour fastness to perspiration(Grade) *AATCC 15-2013(2014)</b> |           |             |         | —         |
| Color change   |           | —           | 4.5     |           |
| Staining   | Acetate   | —           | 4.5     |           |
|  | Cotton    | —           | 4.5     |           |
|  | Polyamide | —           | 4.5     |           |
|  | Polyester | —           | 4.5     |           |
|  | Acrylic   | —           | 4.5     |           |
|  | Wool      | —           | 4.5     |           |
| Self-Staining  |           | —           | 4.5     |           |
| <b>4 Colour fastness to washing(Grade) *AATCC 61-2013e(2020)</b>     |           |             |         | —         |
| Colour change  |           | —           | 4.5     |           |
| Staining   | Acetate   | —           | 4.5     |           |
|  | Cotton    | —           | 4.5     |           |
|  | Polyamide | —           | 4.5     |           |
|  | Polyester | —           | 4.5     |           |
|  | Acrylic   | —           | 4.5     |           |
|  | Wool      | —           | 4.5     |           |
|  |           | —           | 4.5     |           |

Remark: 1A, 45 minutes mechanical wash at 40°C (105°F) in 0.37% AATCC WOB Detergent solution with 10 steel balls.



|   |           | Requirement | Results | Judgement |
|---|-----------|-------------|---------|-----------|
| <b>5 Colour fastness to dry cleaning(Grade) *AATCC 132-2013</b> |           |             |         |           |
| Colour change   |           | —           | 4.5     | —         |
| Staining  | Acetate   | —           | 4.5     |           |
|   | Cotton    | —           | 4.5     |           |
|   | Polyamide | —           | 4.5     |           |
|   | Polyester | —           | 4.5     |           |
|   | Acrylic   | —           | 4.5     |           |
|   | Wool      | —           | 4.5     |           |
| Self-Staining   |           | —           | 4.5     |           |

Sample Photo



\*\*\* End of Report\*\*\*

